This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

1.-19. (Canceled)

- 20. (Previously Presented) A thermoplastic composition comprising a thermoplastic polymer, having incorporated therein a crosslinked phase from a reaction of:
- (A) a copolymer made from ethylene and an unsaturated epoxide, a polyolefin grafted with an unsaturated epoxide, or a product having two epoxide groups,
- (B) a copolymer made from ethylene and an unsaturated carboxylic acid anhydride, and
- (C) a copolymer made from an unsaturated carboxylic acid, or an $\alpha\omega$ aminocarboxylic acid,

wherein the weight ratio of (C)/(B) is 0.2:1 - 0.5:1.

- 21. (Previously Presented) A thermoplastic composition comprising a thermoplastic polymer, having incorporated therein a crosslinked phase from a reaction of:
 - (A) a copolymer made from ethylene/alkyl (meth)acrylate/glycidyl (meth)acrylate,
 - (B) a copolymer made from unsaturated carboxylic acid anhydride, and
- (C) a copolymer made from unsaturated carboxylic acid, or an $\alpha\omega$ aminocarboxylic acid.
- 22. (Previously Presented) A composition according to claim 20, wherein (A) is a copolymer made from ethylene/alkyl (meth)acrylate/glycidyl (meth)acrylate.

23. (Previously Presented) A composition according to claim 20, wherein (A) is either a copolymer made from ethylene and an unsaturated epoxide, a polyolefin grafted with an unsaturated epoxide, or a product having two epoxide groups, and (C) is a partially or completely hydrolyzed copolymer made from ethylene and an unsaturated carboxylic acid anyhdride, a partially or completely hydrolyzed copolymer of a polyolefin grafted with an unsaturated carboxylic acid anhydride, or an α , ω -aminocarboxylic acid.

- 24. (Previously Presented) A composition according to claim 21, wherein (B) is either a copolymer made from ethylene and an unsaturated carboxylic acid anhydride, or a polyolefin grafted with an unsaturated carboxylic acid anhydride, and (C) is a partially or completely hydrolyzed copolymer made from ethylene and an unsaturated carboxylic acid, a partially or completely hydrolyzed copolymer of a polyolefin grafted with an unsaturated carboxylic acid anhydride, or an alpha, α , ω -aminocarboxylic acid.
- 25. (Previously Presented) A composition according to claim 20, wherein (C) is a copolymer made from ethylene/alkyl (meth)acrylate/(meth)acrylic acid.
- 26. (Previously Presented) A composition according to claim 21, wherein (C) is a copolymer made from ethylene/alkyl (meth)acrylate/(meth)acrylic acid.
- 27. (Previously Presented) A composition according to claim 22, wherein (C) is a copolymer made from ethylene/alkyl (meth)acrylate/(meth)acrylic acid.
- 28. (Previously Presented) A composition according to claim 23, wherein (C) is a copolymer made from ethylene/alkyl (meth)acrylate/(meth)acrylic acid.

- 29. (Previously Presented) A composition according to claim 24, wherein (C) is a copolymer made from ethylene/alkyl (meth)acrylate/(meth)acrylic acid.
- 30. (Previously Presented) A composition according to claim 20, wherein the thermoplastic polymer is a polyamide or a saturated polyester.
- 31. (Previously Presented) A composition according to claim 21, wherein the thermoplastic polymer is a polyamide or a saturated polyester.

32. (Canceled)

- 33. (Previously Presented) A composition according to claim 23, wherein (C) is an α -aminocarboxylic acid.
- 34. (Previously Presented) A composition according to claim 23, wherein (C) is an aminoundecanoic acid.

35. (Canceled)

- 36. (Previously Presented) A composition according to claim 23, wherein (C) is said copolymer made from ethylene and unsaturated carboxylic acid.
- 37. (Previously Presented) A composition according to claim 36, wherein (A) is a copolymer made from ethylene and glycidyl methacrylate.

- **38.** (**Previously Presented**) A composition according to claim 20, wherein (B) is a copolymer made from ethylene and maleic anhydride.
- 39. (Previously Presented) A composition according to claim 37, wherein(B) is a copolymer made from ethylene and maleic anhydride.
- 40. (Previously Presented) A composition according to claim 39, wherein (C) is a copolymer made from ethylene/alkyl (meth)acrylate/(meth)acrylic acid.
- 41. (Previously Presented) A thermoplastic composition comprising a thermoplastic polymer, having incorporated therein a crosslinked phase from a reaction of:
- (A) a copolymer of ethylene and an unsaturated epoxide, a polyolefin grafted with an unsaturated epoxide, or a product having two epoxide groups,
 - (B) a copolymer of ethylene and an unsaturated carboxylic acid anhydride, and
- (C) a copolymer of an unsaturated carboxylic acid, or an α,ω -aminocarboxylic acid,

wherein the weight ratio of (C)/(B) is 0.2:1 - 0.5:1.

- 42. (Previously Presented) A thermoplastic composition comprising a thermoplastic polymer, having incorporated therein a crosslinked phase from a reaction of:
 - (A) an ethylene/alkyl (meth)acrylate/glycidyl (meth)acrylate copolymer,

(B) a copolymer of an unsaturated carboxylic acid anhydride, and

(C) a copolymer of an unsaturated carboxylic acid, or an α -aminocarboxylic

acid.

43. (Previously Presented) A composition according to claim 20, wherein

(A) is a copolymer made from ethylene/methyl acrylate/glycidyl methacrylate and, (B) is a

copolymer made from ethylene/ethyl acrylate/maleic anhydride.

44. (Currently Amended) A composition according to claim 43, wherein (C) is a

copolymer made from Θ ethylene/alkyl (meth)acrylate/(meth)acrylic acid, or α , ω -amino

carboxylic acid.

45. (Previously Presented) A thermoplastic composition comprising a

thermoplastic polymer, having incorporated therein a crosslinked phase from a reaction of

components consisting essentially of:

(A) a copolymer made from ethylene and an unsaturated epoxide, a polyolefin

grafted with an unsaturated epoxide, or a product having two epoxide groups,

(B) a copolymer made from ethylene and an unsaturated carboxylic acid

anhydride, and

(C) a copolymer made from an unsaturated carboxylic acid, or an αω-

aminocarboxylic acid,

wherein the weight ratio of (C)/(B) is 0.2:1 - 0.5:1.

- 46. (Previously Presented) A thermoplastic composition comprising a thermoplastic polymer, having incorporated therein a crosslinked phase from a reaction of components consisting of:
- (A) a copolymer made from ethylene and an unsaturated epoxide, a polyolefin grafted with an unsaturated epoxide, or a product having two epoxide groups,
- (B) a copolymer made from ethylene and an unsaturated carboxylic acid anhydride,
- (C) a copolymer made from an unsaturated carboxylic acid, or an α,ω aminocarboxylic acid,

wherein the weight ratio of (C)/(B) is 0.2:1 - 0.5:1.

47. (Previously Presented) A composition according to claim 20, wherein the thermoplastic polymer is a polyamide, (A) is the copolymer made from ethylene and glycidyl methacrylate or the polyolefin is ethylene grafted with glycidyl methacrylate; (B) is the copolymer made from ethylene and maleic anhydride; and (C) is the copolymer made from ethylene and acrylic acid, or ethylene and methacrylic acid.

48.-52. (Canceled)